
Static Shielding Bag 1000 Series

This transparent metal-in static shielding bag is designed to provide a static safe environment for sensitive electronic devices. Bags are printed with an ESD protective symbol and a lot code for traceability. Open top (1000) and ZipTop (3000) styles are available. The bags are heat sealable.

SCS Static Shielding Bags 1000 are manufactured from a polyester, metal, polyethylene laminate. The polyester dielectric in concert with the metal layer provides discharge shielding. The exterior being static dissipative allows electrostatic charges to be removed when grounded.

Open Top Bag ZipTop Bag OFFSET SCS SCS SEAL SEAL Static Shielding Bag Static Shielding Bag 1000 RoHS RoHS LENGTH LENGTH StaticControl.com StaticControl.com Made in America Made in America LOT 01685282606584 LOT 01685282606584 FOLD FOLD WIDTH

Tolerance: Width -0, +1/4" Length +/- 1/8" Offset 0 to 1/4" Seal width 3/8" with a tolerance of +/- 1/8" Note: Standard bag markings shown above and are not to scale.



RoHS 2, REACH, and Conflict Minerals Statement

None of the RoHS 2 restricted materials or REACH substances of very high concern as of 2017/01/12, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See SCS Warranty, Limitation of Liability and Remedies

Meets ANSI/ESD S20.20, Packaging standard ANSI/ESD S541, and Static Control Bag ANSI/ESD S11.4 Level 3



		\ <u></u> /
Physical	Typical Value	Testing Method
Tensile Strength	4600 PSI, 32 MPa	ASTM D882
Puncture Resistance	12 lbs, 53 N	MIL-STD-3010C Method 2065
Seal Strength	11 lbs, 48 N	ASTM D882
Thickness	2.8 mils, 0.071 mm +/-10%	MIL-STD-3010C Method 1003
Marking Adhesion	Pass	IPC-TM-650 2.4.1
Transparency	40%	Tobias
Electrical	Typical Value	Testing Method
ESD Shielding	<10 nJ	ANSI/ESD STM11.31
Surface Resistance - Interior	$1 \times 10^4 \text{ to} < 1 \times 10^{11} \text{ ohms}$	ANSI/ESD STM11.11
Surface Resistance - Exterior	< 1 x 10 ¹¹ ohms	ANSI/ESD STM11.11
Static Decay	< 2 seconds	ETS 406D
Cleanliness	Typical Value	Testing Method
Silicone	Not Detected	FTIR
Heat Sealing Conditions	Typical Value	
Temperature	300°F – 375°F, 149°C – 190°C	
Time	0.5 - 3.5 seconds	
Pressure	30 – 70 PSI, 206 – 482 KPa	

Bag is free of amines, silicones and heavy metals.

This product is intended for commercial use only. This product is not on the Qualified Product Listing under the Defense Standardization Program.



Specifications and procedures subject to change without notice.

1000 SERIES STATIC SHIELDING BAG

